



NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	D12*D9*2 mm
Magnetized direction	Through 2 mm direction
Weight	0.75 g/pc
Pull Force	0.4KG±10%
Br	12.2 KGs
Coercive-Force Hcb	≥11.3 KOe
Intrinsic Coercive Force Hcj	≥12 KOe
(BH) Max	36 MGOe
Working Temperature	≤ 80℃





NINGBO BESTWAY M&E CO., LTD

Add: No. 225 Northern Section of Huancheng West Road, Ningbo, Zhejiang, China

Tel: 86-574-87504597 86-574-27788030 Fax: 86-574-87506697

E-mail: sales9@bwmagnet.com (Samantha) Website: www.bwmagnets.com

Technical Data Sheet

Specification	
Material	NdFeB
Grade	N38
Coating	NI-CU-NI
Size	D15*D8*3 mm
Magnetized direction	Through 3 mm direction
Weight	2.88 g/pc
Pull Force	1 KG $\pm$ 10%
Br	12.2 KGs
Coercive-Force Hcb	$\geq$ 11.3 KOe
Intrinsic Coercive Force Hcj	$\geq$ 12 KOe
(BH) Max	36 MGOe
Working Temperature	$\leq$ 80°C

宁波贝威机电有限公司
NINGBO BESTWAY M&E CO., LTD

吕新民